

# **VDM® Aeterna® 3831**

## **CuZn37Mn3Al2Si**

# VDM® Aeterna® 3831

CuZn37Mn3Al2S

VDM® Aeterna® 3831 is a lead-free brass alloy of CW713R EN Material Nomenclature Group. VDM® Aeterna® alloys are generally used on sliding applications. Because of these good sliding properties, the alloy is increasingly applied in the area of axial piston pumps.

VDM® Aeterna® 3831 alloy is characterized by the following features:

- good sliding properties
- high strength and high hardness
- high wear resistance
- good resistance to aggressive media / oils
- very good machinability

Nomenclature

Standardization	General Material Designation
D	VDM® Aeterna® 3831
EN Material-Nr.:	CW713R lead-free
Description	CuZn37Mn3Al2Si

Table 1 - Nomenclature

# Chemical Composition

	Cu	Zn	Pb	Fe	Mn	Ni	Al	Si	Sn	Other
Min.	57,0	Rem.	-	-	1,3	-	1,3	0,3	-	-
Max.	59,0	Rem.	< 0,1	0,8	3,0	1,1	2,0	1,5	0,5	0,5

Table 2 - Chemical composition, (wt. %)

# Physical Properties

Density	Melting range
8,1 g/cm <sup>3</sup>	880 - 890° C

Temperature	Heat conductivity	Electrical conductivity	Young's modulus	Coefficient of thermal expansion
°C	$\frac{W}{m \cdot K}$	$\frac{MS}{m}$	$\frac{kN}{mm^2}$	$\frac{10^{-6}}{K}$
20	76	10	100	19,5

Table 3 - Typical physical properties of VDM® Aeterna® 3831 alloy

# Mechanical Properties

Condition	Dimention	Yeld strength R <sub>p 0,2</sub>	Tensile strength R <sub>m</sub>	Elongation A5	Brinell-Hardness HB 2,5/62,5
	[mm]	[MPa]	[MPa]	[%]	
R540	Ø 15 - Ø 70	230 - 270	540 - 580	12 - 20	140

Table 4 - Typical mechanical properties of VDM® Aeterna® 3831 alloy

# Applications

Typical areas of application of lead-free VDM® Aeterna® 3831 alloy are:

- Sliding application in general
  - Sliding bearings
  - Synchronizer rings
- Axial piston pumps:
  - Distribution plates
  - Bearing bushes
  - Holding segments

# Imprint

January 2024

**Publisher**

VDM Metals International GmbH  
Plettenberger Straße 2  
58791 Werdohl  
Germany

**Disclaimer**

All information contained in this data sheet are based on the results of research and development work carried out by VDM Metals International GmbH, and the data contained in the specifications and standards listed available at the time of printing. The information does not represent a guarantee of specific properties. VDM Metals reserves the right to change information without notice. All information contained in this data sheet compiled to the best of our knowledge and provided without liability. Deliveries and services are subject exclusively to the relevant contractual conditions and the General Terms and Conditions issued by VDM Metals International GmbH. Use of the most up-to-date version of this data sheet is the responsibility of the customer.

VDM Metals International GmbH  
Engineered Solutions  
Zeilweg 42  
60439 Frankfurt am Main  
Germany

Telefon +49 (0)69 5802-0  
Fax +49 (0)69 5802-159

[es-sales.vdm@vdm-metals.com](mailto:es-sales.vdm@vdm-metals.com)