

**VDM® Aeterna® VL22 3830**  
**CuZn37Mn3Al2PbSi**

# VDM® Aeterna® VL22 3830

## CuZn37Mn3Al2PbSi

VDM® Aeterna® VL22 is a brass alloy of CW713R EN Material Nomenclature Group.

VDM® Aeterna® alloys are generally used on sliding applications. Because of these good sliding properties, the alloy is increasingly applied in the area of axial piston pumps.

The following features characterize VDM® Aeterna® VL22 3830 alloy:

- good sliding properties
- high strength and high hardness
- high wear resistance
- good resistance to aggressive media / oils
- very good machinability

### Nomenclature

Standardization	General Material Designation
D	VDM® Aeterna® VL22 3830
EN Material-Nr.:	CW713R
Description	CuZn37Mn3Al2PbSi

Table 1 - Nomenclature

# Chemical Composition

	Cu	Zn	Pb	Fe	Mn	Ni	Al	Si	Sn	Other
Min.	57,0	Rem.	0,2	-	1,3	-	1,3	0,3	-	-
Max.	59,0	Rem.	0,8	0,8	3,0	1,1	2,0	1,5	0,5	0,3

Table 2 - Chemical composition, (wt. %)

# Physical Properties

Density	Melting range
8,1 g/cm <sup>3</sup>	880 - 890° C

Temperature	Heat conductivity	Electrical conductivity	Young's modulus	Coefficient of thermal expansion
°C	$\frac{W}{m \cdot K}$	$\frac{MS}{m}$	$\frac{kN}{mm^2}$	$\frac{10^{-6}}{K}$
20	76	10	100	19,5

Table 3 - Typical physical properties of VDM® Aeterna® VL22 3830 alloy

# Mechanical Properties

Condition	Dimension	Yield strength	Tensile strength	Elongation	Brinell-Hardness
	[mm]	R <sub>p 0,2</sub> [MPa]	R <sub>m</sub> [MPa]	A5 [%]	HB 2,5/62,5
R590	< Ø 50	270	590	14	150 - 180
R540	Ø 15 - Ø 70	240	540	18	140 - 170
R540	Ø 70 - Ø 100	230	540	12	140 - 170
forged H140	-	(230)	(510)	(12)	> 130

Table 4 - Typical mechanical properties of VDM® Aeterna® VL22 alloy

# Applications

Typical areas of application of VDM® Aeterna® VL22 3830 alloy are:

- Sliding application in general
  - Sliding bearings
  - Synchronizer rings
  
- Axial piston pumps:
  - Distribution plates
  - Bearing bushes
  - Holding segments

# Imprint

December 2022

**Publisher**

VDM Metals International GmbH  
Plettenberger Straße 2  
58791 Werdohl  
Germany

**Disclaimer**

All information contained in this data sheet are based on the results of research and development work carried out by VDM Metals International GmbH, and the data contained in the specifications and standards listed available at the time of printing. The information does not represent a guarantee of specific properties. VDM Metals reserves the right to change information without notice. All information contained in this data sheet compiled to the best of our knowledge and provided without liability. Deliveries and services are subject exclusively to the relevant contractual conditions and the General Terms and Conditions issued by VDM Metals International GmbH. Use of the most up-to-date version of this data sheet is the responsibility of the customer.

VDM Metals International GmbH  
Engineered Solutions  
Zeilweg 42  
60439 Frankfurt am Main  
Germany

Telefon +49 (0)69 5802-0  
Fax +49 (0)69 5802-159

[es-sales.vdm@vdm-metals.com](mailto:es-sales.vdm@vdm-metals.com)